

ACQUARELLO

WET880.XXS.WHT

Waterborne Topcoat for exterior white - Application by brush

Main product characteristics

Typical Proprieties :	High elasticity	High concentration of UV filters	Good touch feeling
Recommended use for :	doors	windows	shutters
Applications Method:	By conventional Spray gun	brush	
Preparation product:	Ready to use. In case of dilution, add up to 5-10% of warm water.		

Gloss levels available

40 gloss	100 gloss		
----------	-----------	--	--

Chemical – Physical characteristics (20 °C)

Solid Content (%)	45 ± 1	Vertical Hold (µm wet)	150
Specific Gravity (g/cm ³)	1,32 ± 0,020	Recommended N° of coats	1 - 2
Viscosity Brookfield /CPS	1500 – 2500	Recommended quantity per coat (gr/m ²)	min: 80 max: 130
		Metric yield (m ² /kg)	5

Application Properties

General information

Dry at 20°C and UR% between 45 - 65: 100 g/m ²		Dry in tunnel: 150 g/m ²		
Dust free	30 minutes		Temperature	Time
Handling	1 hour	Flash Off	30 °C	20 minutes
Overcoat	4 - 6 hours	Laminar Air	45 °C	45 minutes
Stackable	24 hours	Cooling	20 °C	15 minutes
Sanding	4 hours	Stackable	At Tunnel exit	

Substrate Preparation

Wood treated with Isolator: Sand the Isolator (Eco Isoliergrund Bianco or Ecoverniprotect Bianco) using sand paper grit 240-320 and, then, apply 2 coat of Acquarello white.

The application on Nitrocellulose and polyurethane basecoats is not recommended.

Application Instructions

Brush type: use only mixed or synthetic hair.

To obtain the best results it is necessary to use the right equipment in order to better atomize the paint.

Here follows some suggestions for spraying applications:

Use	Dilution %	Nozzle	Press. Air / bar	Press. Vanish / bar
Conventional spray gun	5 - 10	2 - 2,5	3,5	--

The use of pre-atomizers and pre-heaters, to bring the temperature to 30 – 40 °C, ensures a correct application regardless the room temperature. The drying process should be carried out in environments with adequate air ventilation (the recycle of air in the drying room should be carried out every 15-20 minutes)

Note and remarks

- Mix the product before use.
- The shelf life is 12 months if the products are stored in an environment with temperature between 5 - 35°C.
- The product application on substrate must be done in an environment with no less than 12°C. Coatings applied at lower temperatures will show chemical and mechanical properties lower than standard performances that can be normally achieved.
- Coating left overs (washing waters, waters from spray booths, used coatings) must be disposed according to local regulations. Never dispose residues directly into drains.
- Application tools must be cleaned with water after use. When dry films must be removed, the special detergent **HYDROCLEANER** should be used, letting it work overnight and then cleaning with water.

Additives

Problems / Requirements	Solutions	Quantity to be used	
		%	Grams per 25 kg
Craters/Cissing caused by environment contamination	Soluzione Antischivante	0.5 max.	125 grs.
How to increase the verticality	Soluzione Addensante	2 - 5 max	500 -1250 grs.
How to slow down the drying process	WB Retarder	5 - 20 max	1250 - 5000 grs.