

**ECO ULTRATIX**

**WET888.XXS.XXX**

Waterborne Topcoat for exterior

**Main product characteristics**

<b>Typical Proprieties :</b>	High concentration of IPBC	High concentration of UV filters	High outdoor resistance
<b>Recommended use for :</b>	doors	windows	shutters
<b>Applications Method:</b>	By conventional Spray gun	Air less	Air mix
<b>Preparation product:</b>	Ready to use. In case of dilution, add up to 5-10% of warm water		

**Gloss levels available & colours**

Clear 30 gloss	Larch 30 gloss	Hemlock 30 gloss	Teak 30 gloss
Walnut 30 gloss	Clear 50 gloss	Clear 100 gloss	Clear 20 gloss

**Chemical – Physical characteristics (20 °C)**

**Application Properties**

Solid Content (%)	40 ± 1	Vertical Hold (µm wet)	400
Specific Gravity (g/cm <sup>3</sup> )	1,040 ± 0,020	Recommended N° of coats	1 - 2
Viscosity Brookfield /CPS	35000 – 40000 (winter)	Recommended quantity per coat (gr/m <sup>2</sup> )	min: 250 max: 275
Viscosity Brookfield /CPS	50000 – 60000 (summer)	Metric yield (m <sup>2</sup> /kg)	3 - 4

**General information**

Dry at 20°C and UR% between 45 - 65: 100 g/m <sup>2</sup>		Dry in tunnel: 150 g/m <sup>2</sup>		
Dust free	15 minutes		Temperature	Time
Handling	1 hour	Flash Off	30 °C	15 minutes
Overcoat	4-6 hours	Laminar Air	45 °C	90 minutes
Stackable	24 hours	Cooling	20 °C	15 minutes
Sanding	4 hours	Stackable	At Tunnel exit	

**Substrate Preparation**

**Wood treated with basecoat:** Sand the basecoat (Eco Vernifond or Eco Supernova Fond) using sand paper grit 240-320 and, then, apply 1 coat of Eco Ultratix.

The Eco Ultratix suits applications on wood items already coated with preservative, as well.

The application on Nitrocellulose and polyurethane basecoats is not recommended.

**Application Instructions**

To obtain the best results it is necessary to use the right equipment in order to better atomize the varnish.

Here follows some suggestions for spraying applications:

Use	Dilution %	Nozzle	Press. Air / bar	Press. Vanish / bar
Conventional spray gun	5 - 10	2 - 2,5	3 - 4	--
Air mix	--	09 - 11	1 - 2	80 -110
Air less	--	09 - 11	--	120 - 150

The use of pre-atomizers and pre-heaters, to bring the temperature to 30 – 40 °C, ensures a correct application regardless the room temperature. The drying process should be carried out in environments with adequate air ventilation (the recycle of air in the drying room should be carried out every 15-20 minutes).

**Note and remarks**

- Mix the product before use.
- The shelf life is 12 months if the products are stored in an environment with temperature between 5 - 35°C.
- The product application on substrate must be done in an environment with no less than 12°C. Coatings applied at lower temperatures will show chemical and mechanical properties lower than standard performances that can be normally achieved.
- Coating left overs (washing waters, waters from spray booths, used coatings) must be disposed according to local regulations. Never dispose residues directly into drains.
- Application tools must be cleaned with water after use. When dry films must be removed, the special detergent **HYDROCLEANER** should be used, letting it work overnight and then cleaning with water.

**Additives**

Problems / Requirements	Solutions	Quantity to be used	
		%	Grams per 25 kg
Craters/Cissing caused by environment contamination	Soluzione Antischivante	0.5 max.	125 gr.
How to increase the verticality	Soluzione Addensante	2 - 5 max	500 -1250 gr.
How to slow down the drying process	WB Retarder	5 - 20 max	1250 - 5000 gr.